

PN	PN-EN 10088-1	DIN/DIN EN	AISI	UNS	SS	AFNOR	BS
	1.4003	X2CrNi12					
	1.4005	X12 CrS 13	416	S 41600	2380	Z11CF13	416 S 21
1H13	1.4006	X12Cr13	410	S 41000	2302	Z10C13	410 S 21
H17	1.4016	X6 Cr 17	430	S 43000	2320	Z8C17	430 S 15
2H13	1.4021	X20Cr13	420	S 42000	2303	Z20C13	420 S 37
3H13	1.4028	X30Cr13	420 F	S 42020	2304	Z30C13	420 S 45
4H13	1.4034	X46Cr13			(2304)	Z40C14	(420 S 45)
H17N2/2H17N2	1.4057	X17CrNi16-2	431	S 43100	2321	Z15CN 16.02	431 S 29
	1.4104	X14CrMoS17	430 F	S 43020	2383	Z13CF17	(441 S 29)
3H17M	1.4112	X90CrMoV18	440B	S 44003			
0H18N9	1.4122	X39CrMo17-1					
	1.4301	X5CrNi18-10	304	S 30400	2332	Z6CN18.09	304 S 15
	1.4305	X8CrNi18-9	303	S 30300	2346	Z8CNF18.09	303 S 31
00H18N10	1.4306	X2CrNi19-11	304 L	S 30403	2352	Z2CN18.10	304 S 11
	1.4307	X2CrNi18-9	304 L		2352	Z3CN18.10	304 S 11
	1.4310	X10 CrNi 18-8	301	S 30100	2331	Z2CN18.08	301 S 22
	1.4313	X3CrNiMo13-4	CA 6-NM		2384	Z4CND13.04M	425 C 11
	1.4401	X5 CrNiMo 17-12-2	316	S 31600	2347	Z7CND17.12.02	316 S 31
00H17N14M2	1.4404	X2CrNiMo17-12-2	316L	S 31603	2348	Z3CND18.12.02	316 S 11
	1.4418	X4CrNiMo16-5-1			2387	Z6CND16.05.01	
	1.4432	X2 CrNiMo 17-12-	316 L		2353	Z3CND17.12.03	316 S 13
	1.4435	X2CrNiMo18-14-3	316 L	S 31603	2353	Z3CND18.14.03	316 S 11
	1.4436	X3 CrNiMo 17-13-3	316	S 31600	2343	Z7CND18.12.03	316 S 31
	1.4438	X2 CrNiMo 18-15-4	317 L	S 31703	2367	Z3CND19.15.04	317 S 12
	1.4439	X2CrNiMo17-13-5	(317 LMN)				
	1.4449	X5CrNiMo 17-13	317	S-31700			317 S 16
	1.4460	X3CrNiMoN27-5-2	329	S-32900	2324	Z5CND27.05.AZ	
	1.4462	X2CrNiMoN22-5-3		S-31803	2377	(Z5CNDU21.08)	
	1.4529	X1NiCrMoCuN25-20-7		(S 31254)			
0H22N24M4TCu	1.4539	X1NiCrMoCu25-20-5	(904L)	N 08904	2562	Z1NCDU 25.20	
1H18N9T	1.4541	X6CrNiTi18-10	321	S 32100	2337	Z6CNT18.10	321 S 31
	1.4542	X5CrNiCuNb16-4	630	S 17400		Z7CNU15.05	
H17N13M2T	1.4550	X6 CrNiNb 18-10	347	S 34700	2338	Z6CENNb 18.10	347 S 31
	1.4563	X1NiCrMoCu31-27-4		N 08028	2584	Z2NCDU31.27	
	1.4571	X6CrNiMoTi17-12-2	316 Ti	S 31635	2350	Z6CNDT17.12	320 S 31
H25T							
H6S2	1.4713	X10CrAlSi7				Z8CA7	
H13JS	1.4724	X10CrAlSi13				(Z10C13)	
H18JS	1.4742	X10CrAlSi18				Z10CAS18	
H16N36S2	1.4749	X18 CrN 28	446-1	S 44600	2322		
	1.4762	X10 CrAlSi25	(446)	(S 44600)	(2320)	Z10CAS24	
	1.4821	X15 CrNiSi				Z20CNS25.04	
H20N12S2	1.4828	X15CrNiSi 20-12	309	(S 30900)		Z15CNS20.10	309 S 24
H25N20S2	1.4841	X15CrNiSi 25-21	314	S 31400		Z12CNS25.20	314 S 25
H23N18	1.4845	X8CrNi 25-21	310 S	S 31008	2361	Z12CNS25.20	310 S 24
H16N36S2	1.4864	X12NiCrSi35-16	330	N 08303		Z12NCS35.16	(3076 NA 17)
	1.4876	X10NiCrAlTi32-21	B 163			Z8NC32.21	3076 NA 15H
	1.4878	X8CrNiTi18-10	321	S 32100	2337	Z6CNT18.12	321 S 51
	1.4923	X22CrMoV12-1					